



Add some cyclohexane, 2.5% dosage of EC N-100 and 0.45% dosage of polyethylene into retort, then heat until the solution is boiling and completely uniform, then in slow speed mixing until the temperature cooled between 55 — 65 °C, you can add urea and continue to stirring until the temperature cooled at 10 °C you can get initial capsule, then keep on mixing two hours, so you will get product.